

RTV Silicone Adhesives/Sealants

Technical Data				
	RTV102 White	RTV103 Black	RTV106 Red	RTV108 Trans
Min Operating Temp °C	-60	-60	-60	-60
Max Operating Temp °C	204	204	260	204
Specific Gravity	1.05	1.05	1.07	1.05
Shore Hardness A	30	30	30	30
Tensile Strength PSI	400	400	375	400
Elongation %	450	450	400	450
Tear Strength lb/in	45	45	30	45
Dielectric Strength kv/mm	20	20	20	20
Dielectric Constant (at 60Hz)	2.8	2.8	2.8	2.8

All comply with:

FDA 175.300 and 177.1210
MIL A-46106A (1)
UL File No E36952
NSF
USDA

Available in tube or cartridge form.

For a high-strength RTV, we can supply **ELASTOSIL® E43** in cartridge form. This translucent, Industrial strength, self leveling silicone adhesive, is usually available from stock. A Data Sheet for this product is available on request.

Delivery Generally Ex-Stock: 2-3 Days