

SAM-40 Extrusion Grade

High Consistency Silicone Rubber (HCR)

SAMCO[®]
Silicone Products

PRODUCT DATA

MATERIAL REFERENCE:	SAM-40 (HCR Extrusion Grade)
SPECIAL FEATURES:	<ul style="list-style-type: none">• Temperature range from -55 °C to 200 °C• Good blend of physical properties• Complies with BfR and FDA CFR 21 § 177.2600• Meets USP Biological Tests, Classification VI• Meets ISO 10993-1 Biocompatibility Tests• Meets European Pharmacopoeia section 3.1.9
CUSTOMER:	Samco Silicone Products
COLOUR:	Available in all colours

SAFETY INFORMATION

Detailed, safety specific information can be obtained from the Material Safety Data Sheets (MSDS), which are available upon request.

PHYSICAL PROPERTIES

Detailed, safety specific information can be obtained from the Material Safety Data Sheets (MSDS), which are available upon request.

TEST	STANDARD	UNITS	TYPICAL VALUES
Hardness	ISO 48	Shore A	40
Density	ISO 2781	g/cm ³	1.12
Tensile Strength	ISO 37	MPa	10
Elongation @ Break	ISO 37	%	580
Tear Strength	ASTM D 624 B	kN/m	23
Compression Set: (22 Hrs @ 175 °C)	ISO 815-1	%	36

TYPICAL CURE CONDITIONS

Press-Cure	6 minutes @ 115 °C
Post-Cure	4 hours @ 200 °C (in ventilated air)
Catalyst Type	50% paste of bis-(2, 4-dichlorobenzoyl)-peroxide in silicone fluid

This data is obtained from test pieces moulded in the laboratory and are intended as a guide. They should not be used in preparing specifications.